


Etude de : **Sable stabilisé ville de Paris** code : Y35

Agence : SPL Dossier : BRE 07 032
Site : GENNEVILLIERS Date : 1/1/07


DS (t/m3)					OPM	2.03
IPI					0/D	
W (%)					W%	7.5
Densité humide pour compactage chantier					q2	2.12

FORMULE :

0/4 silico-calcaire Yville 47.0%
3/8 silico-calcaire Pont-sur-Yonne 30.0%
0/6.3 Calcaire Authevernes 20.0%
ROC AS 3.0%



Tamis mm	31.5	20.0	10.0	6.3	5.0	4	2.0	1.0	0.500	0.250	0.063
% Passant	100.0	100.0	99.7	83.1	71.1	63.9	54.7	48.1	40.2	19.1	6.4



Observation :